



POLAR INDUSTRIES, Inc.

www.polarindustries.net

PO Box 293
Fisher Branch, MB
R0C 0Z0
Tel: 204-372-8482
Fax: 204-372-8479

Sales Office: 3801 Howell Bend Ct. Oviedo, Fl. 32765 ♦ Tel. (407) 677-6664 ♦ Fax (407) 678-6684

POLAR PREMIUM - 7010 Series

GREEN CONCRETE COAT EPOXY™ - Non VOC

Applications:

7010 is a sprayable one (1) component non-VOC, water resistant, gloss HiOmega Natural Polyurethane epoxy coating cured by sunlight or UV light at 230 – 280

7010 concrete epoxy is designed for application on all concrete , marble, limestone, stone surfaces, indoor and outdoor.

7010 concrete epoxy provides water impermeable coating, heat resistant binding with the concrete. Can fill cracks providing strength and flexibility.

7010 is available in clear and white and can be tinted to a wide variety of custom colours.

PROPERTIES - 7010 Series

Feature	Unit	Value	Measure Method
Pour Point	°C	-10	Factory Prescription
Kin. Viscosity by 23°C	mm ² /s	1344	DIN 53 019
Density sp. Weight	g/cm ³	1069	DIN EN ISO 3675
Working Temperature	45 – 120 °F surface temp	55-77	
Gel time by 23° C (1.5 kg accretion)	min	55	According application
Curing Time	min	30 in sunlight	According application
Set Time	min	4 under UV radiation	
Food Grade			

REMARKS FOR PROCESSING:

The optimal processing temperature is given by $12^{\circ}\text{C} \leq T_p \leq 30^{\circ}\text{C}$.

All devices can be cleaned by acetone or a water/acetone mixture.

POLAR PREMIUM - 7010 Series
GREEN CONCRETE COAT EPOXY™ - Non VOC

RESISTANCE AGAINST CHEMICALS - 7010 Series			
Agent	Findings	Agent	Findings
Solvents Gasoline (Bio) Diesel Methanol Acetone	R R R swelling	Salts NaCl 3 % NaCl Saturated CaCl ₂ Saturated	R R R
Acids HCl H ₃ PO ₄ HCOOH CH ₃ COOH H ₂ SO ₄ HNO ₃	R R R R oxidation oxidation	Lyes NaOH KOH	slow saponification slow saponification
R = Resistant			
DISPOSAL Remains can be chopped up and be composted or burned.			
SAFETY PRECAUTIONS Wear protective clothing (including gloves and goggles). Wash with soap/water or acetone/water after handling.			